



## Technical Data Sheet

**adolin**  
Boyada markanız

### MARMORİNİ - Marble Texture

#### PRODUCT DESCRIPTION

Acrylic copolymer based, marble textured, water based and decorative paint for interior walls.

#### PRODUCT FEATURES

- Ready to use
- Decorative
- Breathable
- No crack formation & flexible
- The glassy surface that it creates is wipeable
- Water-based; no harmful effect to human health and the environment.

#### AREA OF USE

It can be applied onto all "already painted", concrete, plaster, rough cast and betopan coated surfaces following the required leveling and smoothing processes.

#### RECOMENDED APPLICATION

- The application surface should be smooth, robust, moisture-free areas of self-supporting characteristics.
- It is strictly recommended not to prefer satin plaster for surface preparation because of its characteristic and dusting behavior.
- After smoothing the problematic surfaces, ADOLİN İÇ CEPHE GEÇİŞ ASTARI (Interior Wall Transfer Primer) is applied and the surface is left to dry for a minimum 18-24 hours.
- Following the completion of surface preparation works, the first coat of Decolove Marmorini -in the form of plaster- is applied onto the surface by spreading it with a trowel.
- Before drying, the second coat is applied with trowel. The surface area is smoothed from both sides by making circular motions from the outer part into the center area.
- Following the drying of the surface, the third coat can be applied as a patch shape/pattern with a spatula or it is possible to create large effects with a steel trowel.
- Right after the application, it is required to start the polishing process before it dries.
- The polishing process should be carried out cautiously without applying extra pressure onto the surface. Overpressure causes a scratched appearance on the surface area.
- It should be left to dry for 24 hours after the polishing process.

#### TECHNICAL INFORMATION

##### TECHNICAL SPECIFICATIONS

Resin type	Acrylic
Color	See the color catalog
Gloss	Glossy
Viscosity (25°C)	350 ± 25 cPois
Density (20°C)	1,20 ± 2 g/cm

##### DRYING TIMES

(23 ± 2 °C)

Touch Dry	1,2 hours
Recoating tme	4-5 hours
Dust Dry	4-5 hours
Hard dry	12-24 hours

#### PAINTED AREA CONSUMPTION

It may be possible to paint 8 – 10 m<sup>2</sup>/l area per coat depending upon the absorbing capacity of the surface.

#### STORAGE AND PACKAGING INFORMATION

Packaging Information: 3,5Kg 23 Kg  
Storage Conditions: It can be stored for 3 years in its unopened package in a cool and dry environment at a temperature of 5 to 35°C, protecting from frost and direct sunlight.

#### HEALTH AND SAFETY INFORMATION

Pay attention to the health and safety statements on the product packaging. The rules specified in the product safety data sheet must be observed. Contact your nearest health care provider in case of unexpected health problems