

CELLULOSIC FILLER VARNİSH

PRODUCT DESCRIPTION

Alkyd resin-based nitrocellulose modified, air drying wood filler varnish.

PRODUCT FEATURES

- Fast drying
- Easy Sanding
- Excellent spread
- High adhesion strength
- Forms a hard-wearing film.
- Long lasting
- Compatible with polyurethane and acrylic top coat paints

AREA OF USE

It can be used on all kinds of furniture, solid wood, parquet surface.

RECOMENDED APPLICATION

Surface Preparation:

Before application, the surface should be sanded and made dust-free.

Application:

Adolin Cellulosic Filler Varnish is thinned by 25-35% with cellulosic thinner and applied in 2-3 coats with brush. There should be a 15-20-minute interval between the coats and sanding should be performed 4-5 hours after the application of the top coat.

TECHNICAL INFORMATIONS

TECHNICAL SPECIFICATIONS

Resin type	Alkyd+ nitrocellulose
Color	Transparent
Gloss	Semi matt
Gloss (60°C)	40 – 50 Gloss
Viscosity (25°C)	105 ± 5 KU
Density (20°C)	1 ± 0.10 g/ml (White)
Solid matter	41 ± 2 (by weight)
Flash Point	21°C

DRYING TIMES

Touch Dry	10 min.
Recoating tme	15-20 min
Dust Dry	30 min.
Hard dry	3-4 hours

PAINTED AREA CONSUMPTION

Wet film thicknes	: 75 - 80
Dry film thicknes	: 45 - 50
Consumption (m ² /L)	: 10 - 12
Consumption (m ² /Kg)	: 7 – 8

*A controlled sample run should be performed to estimate the precise consumption.

STORAGE AND PACKAGING INFORMATION

Packaging Information: 0,75 Liter, 2,5 Liter, 12 Kg

Storage Conditions: It can be stored for 3 years in its unopened package in a cool and dry environment at a temperature of 5 to 35°C, protecting from frost and direct sunlight.

HEALTH AND SAFETY INFORMATION

Pay attention to the warnings indicated in the precautionary statements of hazards and safety precautions on the product packaging.

The rules specified in the product safety data sheet must be observed.

Contact your nearest health care provider in case of unexpected health problems.