

## PASKES Direct to rust metal paint

### PRODUCT DESCRIPTION

It is a solvent-based, modified alkyd-based, anti-rust, glossy, protective and decorative paint used on interior and exterior metallic surfaces that is applied directly on metal to act as a primer and top coat.

### PRODUCT FEATURES

Direct application on metal	Fast drying
High coverage	Elastic structure
Easy application	Resistant to yellowing
No brush marks	Impact resistant

### AREA OF USE

Adolin Paskes Direct to rust paint can be used safely on all surfaces indoor and outdoor, such as plaster, wood, metal, brick and so on.

### APPLICATION

#### Surface Preparation:

The application surface should be cleaned from all kinds of dirt, oil, dust and loose coatings, and necessary surface correction procedures should be completed. Surface should be sanded and the sanding dust should be cleaned with synthetic thinner.

**Application:** Paskes can be easily applied with brush, roller or spray gun. It should be thinned 5-15% with a synthetic thinner and applied in two coats with 5-6-hour intervals.

### TECHNICAL SPECIFICATIONS

Resin type	Alkyd	<b>Drying Times (at 23 ± 2°C and 50% relative humidity)</b>	
Color	See the color catalog	Touch Dry	2-4 hours
Gloss	85-90 gloss	Dust dry	5-6 hours
Viscosity (KU,25°C)	135 ± 5	Recoating time	6-8 hours
Density (g/cm <sup>3</sup> , 20°C)	1,15 ± 0.05	Hard dry	12-18 hours
Solid Matter	60 ± 2 g/cm		
Flash Point	42°C		

### PAINTED AREA - CONSUMPTION

In two coats, depending on the surface;  
 4-5 m<sup>2</sup> surface can be painted with 0.75 Liter.  
 16-18 m<sup>2</sup> surface can be painted with 2.5 Liter.  
 70-80 m<sup>2</sup> surface can be painted with 12 Liter.

Consumption: 140-160 g/m<sup>2</sup>, 110-125 ml/m<sup>2</sup>

\*A controlled sample run should be performed to estimate the precise consumption.

### STORAGE AND PACKAGING INFORMATION

Packaging Information: 0.75 Liter, 2.5 Liter, 15 Liter

Storage Conditions: It can be stored for 3 years in its unopened package in a cool and dry environment at a temperature of 5 to 35°C, protecting from frost and direct sunlight.

### HEALTH AND SAFETY INFORMATION

Pay attention to the warnings indicated in the precautionary statements of hazards and safety precautions on the product packaging. The rules specified in the product safety data sheet must be observed. Contact your nearest health care provider in case of unexpected health problems.