

CELLULOSIC MATT VARNISH

PRODUCT DESCRIPTION

Alkyd resin-based nitrocellulose modified, air drying, matt wood varnish.

PRODUCT FEATURES

- Fast drying
- Silky matt
- Excellent spread
- Easy application

AREA OF USE

It is used as a top coat varnish for all kinds of furniture applications.

RECOMMENDED APPLICATION

Surface Preparation:

The surfaces prepared with polyurethane or cellulosic matt varnish should be cured and sanded with 220 Grit and 400 Grit sandpaper, respectively. The surface should be made free of sanding dust before applying the topcoat.

Application:

Adolin Cellulosic Matt Varnish should be thinned by 15-20% with cellulosic thinner and applied in 1-2 cross coats with spray gun. An interval of at least 20 - 30 minutes should be allowed between coats for evaporation of thinner.

TECHNICAL INFORMATION

TECHNICAL SPECIFICATIONS

Resin type	Alkyd+ nitrocellulose
Color	Transparent
Gloss	Matt
Gloss (60°C)	5-7 Gloss
Viscosity (25°C)	85 ± 5 KU
Density (20°C)	0,98 ± 0.10 g/ml (White)
Solid matter	33 ± 2 (by weight)
Flash Point	21°C

DRYING TIMES

Touch Dry	5 min.
Recoating time	10 min
Dust Dry	30 min.
Hard dry	2-4 hours

PAINTED AREA CONSUMPTION

Wet film thickness	: 75 - 80
Dry film thickness	: 45 - 50
Consumption (m ² /L)	: 10 - 12
Consumption (m ² /Kg)	: 7 - 8

*A controlled sample run should be performed to estimate the precise consumption.

STORAGE AND PACKAGING INFORMATION

Packaging Information: 0,75 Liter, 2,5 Liter, 12 Kg

Storage Conditions: It can be stored for 3 years in its unopened package in a cool and dry environment at a temperature of 5 to 35°C, protecting from frost and direct sunlight.

HEALTH AND SAFETY INFORMATION

Pay attention to the warnings indicated in the precautionary statements of hazards and safety precautions on the product packaging.

The rules specified in the product safety data sheet must be observed.

Contact your nearest health care provider in case of unexpected health problems.