

CELLULOSIC PRIMER

PRODUCT DESCRIPTION

Alkyd resin-based nitrocellulose modified, air drying primer.

PRODUCT FEATURES

- Fast drying
- Matt appearance
- Excellent spread
- High coverage
- Resistant to physical effects and impacts
- Forms a hard-wearing film.
- Easy Sanding

AREA OF USE

It is used as a top coat paint for all kinds of metal and furniture applications

RECOMENDED APPLICATION

Surface Preparation:

The surface should be cleaned from dust, rust, grease and oil, and care should be taken to ensure that the surface is dry before application..

Application:

Adolin Cellulosic Primer should be thinned by 35-40% with cellulosic thinner and applied in 2-3 cross coats with spray gun. An interval of at least 5 minutes should be allowed between coats for evaporation of thinner. It can be sanded after 3 hours.

TECHNICAL INFORMATION

TECHNICAL SPECIFICATIONS

Resin type	Alkyd+ nitrocellulose
Color	White,Ral7004,Dark gray
Gloss	Matt
Gloss (60°C)	2 – 3 Gloss
Viscosity (25°C)	100 ± 5 KU
Density (20°C)	1,45 ± 0.10 g/ml (White)
Solid matter	60 ± 2 (by weight)
Flash Point	21°C

DRYING TIMES

Touch Dry	10 min.
Recoating tme	5 -10 min
Dust Dry	30 min.
Hard dry	1-2 hours

PAINTED AREA CONSUMPTION

Wet film thicknes	: 75 - 80
Dry film thicknes	: 45 - 50
Consumption (m ² /L)	: 10 - 12
Consumption (m ² /Kg)	: 7 – 8

*A controlled sample run should be performed to estimate the precise consumption.

STORAGE AND PACKAGING INFORMATION

Packaging Information: 0,75 Liter, 2,5 Liter, 12 Kg

Storage Conditions: It can be stored for 3 years in its unopened package in a cool and dry environment at a temperature of 5 to 35°C, protecting from frost and direct sunlight.

HEALTH AND SAFETY INFORMATION

Pay attention to the warnings indicated in the precautionary statements of hazards and safety precautions on the product packaging.

The rules specified in the product safety data sheet must be observed.

Contact your nearest health care provider in case of unexpected health problems.