

**RAPID INDUSTRIAL PRIMER**

**PRODUCT DESCRIPTION**

Styrene alkyd resin-based primer

**PRODUCT FEATURES**

- Fast drying
- High coverage
- Easy application
- Matt appearance
- Good adhesion to metallic surfaces
- Easy application

**AREA OF USE**

It can be used safely for painting of machinery, agricultural, home, garden tools, on surfaces such as , tractor, trailer, auto radiator components, on all kinds of metal parts such as barrels, valves, steel cupboards and steel tables.

**RECOMENDED APPLICATION**

**Surface Preparation:** Before application, the surface should be cleaned from dust, rust, grease and oil, should be sanded at least at ST2 and primer application should be performed.

**Application:** Industrial Primer should be thinned by 30-40% with industrial thinner and should be applied with spray gun angle of 40° to 80°. Top coat application is recommended to be done after 1 day.

**TECHNICAL INFORMATIONS**

TECHNICAL SPECIFICATIONS	
Resin type	Alkyd
Color	Gray,Dark Gray,Red Ral7004
Gloss	Matt
Gloss (60°C)	4 - 7
Viscosity (25°C)	100 ± 2 KU
Density (20°C)	1,60 ± 0.05 g/ml (White)
Solid matter	73 ± 2 (by weight)
Flash Point	21°C

DRYING TIMES	
Touch Dry	20 min.
Recoating tme	40 min.
Dust Dry	1-2 hours
Hard dry	2-3 hours

**PAINTED AREA CONSUMPTION**

Wet film thicknes	: 75 - 80
Dry film thicknes	: 45 - 50
Consumption (m <sup>2</sup> /L)	: 12 - 13
Consumption (m <sup>2</sup> /Kg)	: 8 - 9

**STORAGE AND PACKAGING INFORMATION**

Packaging Information: 0,75 Liter, 2,5 Liter, 15 Kg

Storage Conditions: It can be stored for 3 years in its unopened package in a cool and dry environment at a temperature of 5 to 35°C, protecting from frost and direct sunlight.

**HEALTH AND SAFETY INFORMATION**

Pay attention to the warnings indicated in the precautionary statements of hazards and safety precautions on the product packaging.

The rules specified in the product safety data sheet must be observed.

Contact your nearest health care provider in case of unexpected health problems.