



PASSING & TRANSFORMATION PRIMER

PRODUCT DESCRIPTION

It is a water-based, acrylic resin-based primer developed for previously painted surfaces.

PRODUCT FEATURES

Silicone added	Easy application
Long lasting	Breathable
Four-season application	No bubbling
Water-repellent	Odorless

AREA OF USE

It can be safely used on interior and exterior facades, on all kinds of surfaces such as exposed concrete, coating, plaster, plate.

APPLICATION

Surface Preparation:

All kinds of dirt, oil, dust and loose material should be removed from the application surface, and places that require repairing should be repaired, surfaces previously coated with solvent-based coatings should be roughened with the help of sandpaper and made dust-free.

Application: Transition Transfer Primer is thinned by 10% with water and applied in one coat with brush or roller.

TECHNICAL SPECIFICATIONS

Resin type	Acrylic copolymer	Drying Times (at 23 ± 2°C and 50% relative humidity)	
Color	Transparent	Touch Dry	1-2 hours
Gloss	Glossy	Dust dry	3-4 hours
Viscosity (cPois at 25°C)	180 ± 25	Hard dry	12 hours
Density (g/cm ³ , 20°C)	1.59 g/cm ³		
Solid Matter	65 ± 2 g/cm		

PAINTED AREA - CONSUMPTION

In a single coat, depending on the type of surface;
25 m² surface can be primed with 3.5 Kg.
70 m² surface can be primed with 10 Kg.
140 m² surface can be primed with 20 Kg.

Consumption: 150-200 g/m², 100-140 ml/m²

*A controlled sample run should be performed to estimate the precise consumption.

STORAGE AND PACKAGING INFORMATION

Packaging Information: Packaging Information: 13.5 Kg, 10 Kg, 20 Kg

Storage Conditions: It can be stored for 3 years in its unopened package in a cool and dry environment at a temperature of 5 to 35°C, protecting from frost and direct sunlight.

HEALTH AND SAFETY INFORMATION

Pay attention to the health and safety statements on the product packaging. The rules specified in the product safety data sheet must be observed. Contact your nearest health care provider in case of unexpected health problems.

TSE CLASSIFICATION

Complies with TS 7847. TSE Certified.